

Evaluation Report CCMC 13606-R Weatherdek Plus

07 54 19.01
2013-08-04
2016-06-23
2019-08-14

1. Opinion

It is the opinion of the Canadian Construction Materials Centre (CCMC) that "Weatherdek Plus", when used as a waterproof membrane covering for decks and balconies subject to light pedestrian traffic in accordance with the conditions and limitations stated in Section 3 of this Report, complies with the National Building Code (NBC) of Canada 2015:

- Clause 1.2.1.1.(1)(b), Division A, as an alternative solution that achieves at least the minimum level of performance required by Division B in the areas defined by the objectives and functional statements attributed to the following applicable acceptable solutions:
 - Section 9.26., Roofing

This opinion is based on CCMC's evaluation of the technical evidence in Section 4 provided by the Report Holder.

Ruling No. 14-209-305 (13606-R) authorizing the use of this in Ontario, subject to the terms and conditions contained in the Ruling, was made by the Minister of Municipal Affairs and Housing on 214-09-25 pursuant to s.29 of the *Building Code Act*, 1992 (see ruling for terms and conditions). This Ruling is subject to periodic revisions and updates.

2. Description

The product is a polyvinyl chloride membrane made with a nominal thickness of 1.5 mm. The product is made with reinforced woven and non-woven heat set polyester backings. The surface of the product is embossed to provide a textured finish. The membrane is available in rolls that are 1 372 mm or 1 829 mm wide and can be cut to a required length. The product is available in a variety of colours.

3. Conditions and Limitations

CCMC's compliance opinion in Section 1 is bound by the "Weatherdek Plus" being used in accordance with the conditions and limitations set out below:

- The product can be used as a waterproof membrane that is fully adhered to a continuous solid substrate, such as a plywood or concrete deck and balconies that are subject to light pedestrian traffic.
- The product must be used only in conjunction with plywood or concrete substrates. The membrane must be fully adhered to the substrate with adhesives WD-1000 or WD-7633 and applied as per the installation manual.
- The product's deck membrane can be considered as an alternative solution to materials referenced in Section 9.26. of Division B of the NBC 2015.
- The product is limited for use in areas that are subject to traffic loads generated by residential occupancies only.
- The product must not be exposed to chemical attack or spillage. In situations where extended contact with chemicals or pollutants may occur, the suitability of the product must be determined.
- The product is limited for use where the roof or deck surface has a minimum slope of 1:48.
- Any physical or chemical damage to the membrane must be repaired in accordance with the manufacturer's instructions. The product must not be installed with butt seam joints.
- Joints must be shingle-lapped in order to shed water.
- The product must be installed by approved applicators only and in strict conformance with the manufacturer's installation instructions.

• The product or its packaging must be identified with the manufacturer's name or logo and the phrase "CCMC 13606-R."

4. Technical Evidence

The Report Holder has submitted technical documentation for CCMC's evaluation. Testing was conducted at laboratories recognized by CCMC. The corresponding technical evidence for this product is summarized below.

4.1 Material Requirements

Table 4.1.1 Results of Testing the Material Properties of the Product

D uon ontri	TT:4	Deguinement	Result		
Property	Umt	Kequirement	Woven	Non-woven	
Overall thickness	mm	Report value	1.9	2.0	
Coating thickness	mm	Min. 0.4 (no measurement less than 0.32)	No coating on membrane	No coating on membrane	

4.2 Performance Requirements

Table 4.2.1 Results of Testing the Per	formance Properties of the Product
--	------------------------------------

Property		Unit	Deguinement	Result	
			Kequirement	Woven	Non-woven
Breaking strength		kN/m	> 20	66	67
			<i>≥</i> 30	65	70
Water vapour transmission		g/m²/d	≤4.0	0.7	0.8
Water absorption mass		%	≤ 3.0	1.8	1.7
Static puncture (rating)		-	≥ 3	4	4
Dynamic puncture (rating)		-	≥ 3	4	4
T	original		0	Pass	Pass
Low temperature impact	after weathering	_	8 out of 10 pass	Pass	Pass
	original		Material must not – crack or exhibit any	Pass	Pass
Low temperature flexibility	after heat aging	- 1		Pass	Pass
	after weathering		visible defects.	Pass	Pass
. , , .	machine direction	0/	Min. 75% of original	Pass	Pass
Lap joint strain energy	cross-machine direction	%	membrane	Pass	Pass
Lap joint strain energy –	machine direction	0/	Min. 70% of original	Pass	Pass
(after 7 days boiling)	cross-machine direction	% membrane	membrane	Pass	Pass
Abrasion resistance –	weight loss	g	≤ 0.4	0.4	0.4
original	depth of wear	mm	≤ 0.30	0.17	0.17
Resistance to accelerated we	athering	_	No cracking, blistering or colour change	Pass Pass	
Adhesion substrate	concrete surface with contact adhesive	N		126	219
	plywood substrate with contact adhesive	≥ 125	193	226	
	plywood substrate with latex adhesive			133	128
Slip resistance – dry	leather	_	≥ 0.50	0	54
condition (rating)	rubber		≥ 0.70	0	99

Duono		Unit Dog	Dequinement	Result	
rroperty		Um	Kequirement	Woven	Non-woven
Slip resistance – wet condition (rating)	leather		≥ 0.60	0.6	5
	rubber	_	≥ 0.65	0.8	0

Report Holder

ADS Weatherdek Canada Ltd. 600 Adams Road Kelowna, BC V1X 7S1

Telephone:	1-800-667-2596
	250-765-5575
Fax:	250-765-5548
Email:	info@weatherdek.com
Web site:	www.weatherdek.com

Plant

Winchester, VA, USA

Disclaimer

This Report is issued by the Canadian Construction Materials Centre, a program of NRC Construction at the National Research Council of Canada. The Report must be read in the context of the entire CCMC Registry of Product Evaluations, including, without limitation, the introduction therein which sets out important information concerning the interpretation and use of CCMC Evaluation Reports.

Readers must confirm that the Report is current and has not been withdrawn or superseded by a later issue. Please refer to <u>http://www.nrc-cnrc.gc.ca/eng/solutions/</u> <u>advisory/ccmc_index.html</u>, or contact the Canadian Construction Materials Centre, NRC Construction, National Research Council of Canada, 1200 Montreal Road, Ottawa, Ontario, K1A 0R6. Telephone (613) 993-6189. Fax (613) 952-0268.

NRC has evaluated the material, product, system or service described herein only for those characteristics stated herein. The information and opinions in this Report are directed to those who have the appropriate degree of experience to use and apply its contents. This Report is provided without representation, warranty, or guarantee of any kind, expressed, or implied, and the National Research Council of Canada (NRC) provides no endorsement for any evaluated material, product, system or service described herein. NRC accepts no responsibility whatsoever arising in any way from any and all use and reliance on the information contained in this Report. NRC is not undertaking to render professional or other services on behalf of any person or entity nor to perform any duty owed by any person or entity to another person or entity.

Date modified: 2016-07-04